

K.D. Langley Fiber Services

P.O. Box 7, Tiverton, RI 02878 • Telephone (401) 624-6868

July 24, 2006

Mr. James F. Casale
The Knit With
8226 Germantown Avenue
Chestnut Hill, PA 19118-3402

Report on the Quantitative Fiber Analysis of Yarns

Material Submitted

Brand Name	Yarn Name	Country of Origin	Labeled Composition	Other Identifying Data
Noro	Amagi	Japan	30% Cashmere, 30% Silk 40% Lambswool	100 m/ 40g; No. 3, Lot A
Noro	Cash Iroha	Japan	40% Silk, 30% Lambswool, 20% Cashmere, 10% Nylon	91 m/ 40g; No. 1, Lot A


Laboratory Procedure

Fibers were sectioned with a fiber cutter, and mounted on microscope slides. Over 1000 fibers from each sample were identified using light microscopy at a magnification of 250-400X. These (two) yarns were tested according to AATCC (American Association of Textile Chemists and Colorists) protocols 20-2004 Fiber Analysis: Qualitative, and 20A-2000: Quantitative (reference: sections 12.3, 12.5, 13.) which are generally accepted in the fiber and testing fields as reliable and definitive to determine whether a yarn contains the fibers claimed on its labeling as required by and in accordance with The Wool Products Labeling Act.

Results	Fiber Content (%)	
	Amagi	Cash Iroha
Wool	51.3	37.5
Silk	31.2	38.9
Cashmere	17.5	12.8
Nylon	--	10.8

The opinion expressed in this report is expressed to a reasonable degree of scientific certainty based upon the tests performed and my knowledge and experience in the field of fiber testing.

Sincerely yours,



Kenneth D. Langley